

Twin-V-belts


PU75A red smooth



approx. 80° Shore A










Recommended pretension 3...6 %

Order No.	Profile dimension mm	Cross section cm ²	approx. weight kg/100m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)	
				m	ft	mm	inch	kg	lbs
FBSP75A21X8	21 x 8	1,2	14,0	30	100	60	2,3	23,0	50,6




Coeff. of friction μ : Steel: approx. 0,70 | PE: approx. 0,40 | HDPE: approx. 0,35

Symbols

								
Antistatic profile with outstanding mechanical properties.	Profile with exceptional low-temperature flexibility down to -30°C.	Patented material formulation „PLUS“ for lower product elongation.	Very good UV resistance.	Profiles with FDA/EC conformity for direct contact with food.	Metal and X-ray detectable profiles for maximum food safety.	Hydrolysis resistance (HY). Suitable for humid environments.	Microbe-resistant materials do not provide a breeding ground for microorganisms	Belt made of 2 components enables combination of hardness and features.

Twin-V-belts


PU75A sky blue smooth



approx. 80° Shore A










Recommended pretension 3...6 %

Order No.	Profile dimension mm	Cross section cm ²	approx. weight kg/100m	Standard Roll		Recommended Min. pulley Ø		Fmax/belt (Standard)	
				m	ft	mm	inch	kg	lbs
FBSI30X8LG	30 x 8	1,9	22,4	50	164	60	2,3	45,5	100,1



Coeff. of friction μ : Steel: approx. 0,70 | PE: approx. 0,40 | HDPE: approx. 0,35

Symbols

								
Antistatic profile with outstanding mechanical properties.	Profile with exceptional low-temperature flexibility down to -30°C.	Patented material formulation „PLUS“ for lower product elongation.	Very good UV resistance.	Profiles with FDA/EC conformity for direct contact with food.	Metal and X-ray detectable profiles for maximum food safety.	Hydrolysis resistance (HY). Suitable for humid environments.	Microbe-resistant materials do not provide a breeding ground for microorganisms	Belt made of 2 components enables combination of hardness and features.